

TECHNICAL SHEET

STREŠNA LEPENKA

Bitumen membrane with cardboard reinforcement and oxidized bitumen

Product description

STREŠNA LEPENKA is a waterproofing membrane made from a cardboard reinforcement, totally impregnated and on both sides coated with oxidized bitumen. The membrane is on both sides protected by fine sand.

Characteristics of the

STREŠNA LEPENKA meets the demands of the standard EN 13859-1 type W1.

product

Characteristic	EN Method	Unit	Value	
Reinforcement	Cardboard			
Surface protection		sand / sand		
Length	1848-1	m	≥ 10	
Width	1848-1	m	0,995 to 1,015	
Thickness	1848-1	mm	≥ 1,3	
Mass per unit area	1849-1	kg/m²	≥ 1,3	
Straightness	1848-1	30mm/10m	pass	
Resistance to water penetration	1928	class	W1	
Resistance to water penetration after artificial ageing by long term exposure to elevated temperature (12 weeks at 70 ° C)	1296/1928	class	W1	
Flexibility at low temperature	1109	°C	<u><</u> +4	
Resistance to tearing In longitudinal transversal	12310-1	N	≥ 50 ≥ 50	
Dimensional stability • longitudinal • transversal	1107-1	%	≤ 0,6 ≤ 0,6	
Water vapor transmission properties	1931	m	40 ±10	
Reaction to fire	13501-1	class	F	
Chemical resistance	1847/13969 Annex A	1	pass	
Tensile properties • longitudinal • transversal	12311-1	N/50mm	≥ 250 ≥ 150	
Tensile properties after artificial ageing by long term exposure to elevated temperature (12 weeks at 70°C) • longitudinal • transversal	12311-1	N/50mm	≥ 200 ≥ 100	
Elongation • longitudinal • transversal	12311-1	%/50mm	≥ 1,0 ≥ 1,0	
Elongation after artificial ageing by long term exposure to elevated Temperature (12 weeks at 70°C) • longitudinal • transversal	12311-1	%/50mm	≥ 1,0 ≥ 1,0	
Content of dangerous substances	Annex ZA	1	no	

^{*} NPD – no performance determined

Replace:18-01 21.12.2022 22-01



Use and installation

STREŠNA LEPENKA is used as underlay in systems of pitch roofs, or as temporary protection against dampness. The product is mechanically installed on boarded surfaces with 10 cm overlaps. The product is not resistant against weather influences; therefore, it is necessary to protect it with the primary roofing as quick as possible.

Storage

The rolls must be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

Disposal considerations of waste

For the removal of waste of product, it is necessary to follow the valid local environmental regulations. Waste classification: 17 03 02 bituminous mixtures other than those mentioned in 17 03 01.



The product is in conformity with EN 13859-1:2010 type W1.

The system of quality and handling of the environment is conforming with EN ISO 9001 and EN ISO 14001.

Replace:18-01 21.12.2022 22-01